

SIGOL

Two-component epoxy-polyurethane adhesive for wooden floors



Description

SIGOL is an odorless free of solvents and water two-component epoxy-polyurethane adhesive. **Destinations:** suitable to lay all kinds of wood in any size including solid and engineered floors, without requiring the pre-laying of wood joists and, with previous suitable treatment, onto not absorbing preexisting subfloors (ceramics, tiles, marble, palladian, gres, ect.). Also suitable, but non suitable, for gluing onto heated subfloors.

Characteristics

Mixture ratio	9/1
Application temperature	+10°C ÷ +25°C
Application	notched trowel n. 5
Pot-Life	2 h ⁽¹⁾
Hardening	36/48 h ⁽¹⁾
Coverage	1300-1900 g/m ² depending on the subfloor.
Colour	oak, walnut
Storage stability	1 year ⁽²⁾
Packaging	10 Kg (9+1) - 5 Kg (4,5+0,5)
Tool cleaning	DILUENTE DS (before the hardening of the adhesive)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

Laying conditions

Subfloor

dry, clean, no-dust creating, not too rough.

Humidity of subfloor

2,0% max with cement subfloors.

1,7% max with radiant heating cement subfloors.

0,5% max with anhydrite subfloors

0,2% max with radiant heating anhydrite subfloors

Wood humidity

9%±2

Other uses

Adhering of heat and sound insulating panels (cork, expanded polyurethane, rock-wool).

Adhering of tiles on asbestos cement and chipboards.

Adhering of wood and building materials (ceramics, stoneware-marble tiles) on to metal bases.

How to use

After mixing the two components, spread SIGOL with a notched trowel uniformly on a clean subfloor embodying possible dust

present on it. Proceed with the laying ensuring that the wood tiles are put together properly and gently hammered so as to make the adhesive adhere well to the whole surface. Perfect adhesion to the subfloor is ensured if at least 65% of each wooden component is in direct contact with the adhesive.

In presence of dust-creating and porous subfloors, we recommend to apply first one coat of PRYMER A, PRYMER PUB 77, PRYMER SF 1105, PRYMER FAST 500 or PRYMER 100 (see technical data sheets). After the complete drying of the treatment proceed with the application of the adhesive.

In presence of humid subfloors, we recommend to apply first PRYMER PUB 77, PRYMER SF 1105, PRYMER FAST 500, PRYMER 100, PRYMER EPOX WETT or PRYMER WB 328 S (see technical data sheets). We do not recommend to dip the heads of the tiles into the SIGOL while laying them. If need be, dip the heads of the tiles into a vynilic (PARKETKOLL) adhesive which has a very strong wood to wood adhesion avoiding also the typical "skidding" of the tiles.

If the parquet is to be laid on glassy surfaces (ceramic tiles, enamelled tiles, polished marble, etc.), remove and clean the surface from dust, grit, glue and waxes. Apply by cloth the adhesion promoter DILUENTE APA (see technical data sheet) following the correct application time, than apply SIGOL.

In case of anhydrite subfloors, thoroughly sand using 24 or 36 grit sandpaper; remove dust and apply primer using PRYMER SF 1105 (do not dilute) or PRYMER PUB 77 with DILUENTE DMC 50 thinner at a ratio 70:30. Apply SIGOL and the next sanding should take place after 3-4 days, depending on the atmospheric conditions and humidity level of the wood species used.

When laying down pre-lacquered wooden floors, if a wood piece gets accidentally dirty with glue, clean immediately with DILUENTE PULIPAR or PULIPAR W (see technical data sheets). We recommend, while using SIGOL, to use all the personal prevention systems.

Preparation of synthetic mortars

SIGOL can be used as levelling compound for synthetic mortars preparation. SIGOL mixed with DILUENTE DS (see relative TDS for checking correct ratio) can be added with QUARZ (see relative TDS) until you obtain a synthetic mortar. The suggested mixing ratio is: 9:1 (SIGOL) : 1 (DILUENTE DS) : 10 (QUARZ).

Note:

Do not apply SIGOL in presence of high evaporative fluxes as they cause the increase of pH of the substrate (pH>=10) and they cause problems with the screed/glue/wood system. In case of doubt apply one coat of PRYMER SF 1105 (see technical data sheet) and after 24 hours proceed with the application of SIGOL.

Shipping notes.

If the storage temperature exceeds +25°C, the time of storage is noticeably reduced, at temperatures above +50°C there is a

SIGOL

Two-component epoxy-polyurethane adhesive for wooden floors



real risk of thickening/gelatinization of the product even in the original packaging. For transport by sea it's advisable to use the special thermo-containers.

Label elements

Comp.A	<ul style="list-style-type: none"> - Causes serious eye irritation.- Causes skin irritation.- May cause an allergic skin reaction.- Harmful to aquatic life with long lasting effects. - Contains epoxy constituents. May produce an allergic reaction.- Contains CASHEW SHELL OIL OXIRANE; MONO[(C12-14-ALKYLOXY)METHYL] DERIVS. May produce an allergic reaction. - If medical advice is needed, have product container or label at hand.- Keep out of reach of children.- Contaminated work clothing should not be allowed out of the workplace.- Avoid release to the environment.- Wear protective gloves / protective clothing / eye protection / face protection.- Dispose your waste in dedicated collection points. <p>Contents:REACTION PRODUCT: BISPHENOL A-(EPICHLORHYDRIN); CASHEW SHELL OIL ;</p>
Comp.B	<ul style="list-style-type: none"> - Causes severe skin burns and eye damage.- May cause respiratory irritation.- May cause an allergic skin reaction. - If medical advice is needed, have product container or label at hand.- Keep out of reach of children.- Do not breathe dust / fume / gas / mist / vapours / spray.- Wear protective gloves / protective clothing / eye protection / face protection.- Immediately call a POISON CENTER or doctor / physician.- Store in a well-ventilated place. Keep container tightly closed.- Dispose your waste in dedicated collection points. <p>Contents:2,4,6-TRIS(DIMETHYLAMINOMETHYL) PHENOL; Reaction products of tall oil fatty acids with tetraethylenepentamine ;</p>

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_SIGOL.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.